



ELASTOCOTE

- DESCRIPTION:** California Stucco Elastocote is an acrylic polymer coating available in white and a wide variety of integral colors. Custom color service is available.
- USES:** California Stucco Elastocote can be used to provide aesthetically fresh, clean surface over many types of substrates. Ideal for detail work and reviving aged stucco. Can also be used as a primer and sealer for white Texture-Flex.
- SUBSTRATES:** California Stucco Elastocote must be applied over clean, dry substrates free from all dirt, grease, efflorescence, mildew, paint, etc. Masonry, brick, block, concrete, stucco, Texture-Flex, Roll-Flex and Elastocote are all acceptable substrates.
- COVERAGE:** California Stucco Elastocote comes in one and five gallon containers and will yield approximately 500 square feet per five gallons depending on substrate porosity and texture. At 500 square feet, Elastocote dries to approximately 3.5 mils. One or two coat application must be determined on site. No sealer is necessary.
- ADHESION:** California Stucco Elastocote maintains excellent adhesion to approved and properly prepared substrates.
- CURING TIME:** Initial set in approximately 30 minutes, firm in 24 hours. Final set in 2 weeks.
- SOLUBILITY:** California Stucco Elastocote can be easily cleaned from tools and brushes with soap and water directly after use.
- STORAGE:** Store containers in a cool dry area out of direct sunlight. Keep from freezing. Close container after each use. Keep out of reach of children.
- LIMITATIONS:** California Stucco Elastocote should be applied only to frost-free and unfrozen surfaces above 40 degrees Fahrenheit. If ambient temperature should fall below 40 degrees Fahrenheit, weather protection must be supplied. Do not allow finish material to freeze. Finish material must be protected from rain. Elastocote should not be used on a horizontal surface where water will collect. BASEs must cure out 80% of their moisture content, before applying finish materials.
Do not apply to retaining walls or over Galvanized accessories.
- MIXING:** Do not add water to the finish mix. Mix thoroughly before using.
- APPLICATION:** California Stucco Elastocote can be applied liberally with brush, spray or roller technique. Do not apply when temperature is below 40 degrees Fahrenheit for two consecutive days and finish must be protected from moisture for one day after application.
- WATER VAPOR PERMEABILITY:** California Stucco Elastocote does not act as a vapor barrier.
- WATER VAPOR TRANSMISSION TEST:** See Index #3 – Texture-Flex.